



# Technical Data Sheet

## Pro Image

### Product Features

Pro Image is a single-component, water-based, topcoat for hardwood floors. It provides exceptional durability for the professional or DIY user with minimal odor and fast dry times. Most importantly, it exceeds MFMA standards for slip resistance.

### Recommended Uses

Interior hardwood floors

### Complies w/ the following air quality regulations:

SCAQMD, CARB, Canada, OTC Phase I & Phase II

**Application Conditions:** Recommended 70°F and 50% humidity, out of direct sunlight. Taking surface moisture meter readings is highly recommended before and during application. Variations in conditions and application technique can significantly affect dry times and coverage. Use GF Extender in warm or dry conditions.

**Surface Prep:** Always ensure the surface is clean of contaminants and dust. Remove dust using a vacuum and water-dampened cloth. Sanding any surface too smoothly can reduce adhesion and create application issues like orange peel.

**Raw Wood:** Sand with no finer than 220 grit. Ensure any freshly stained surface has dried thoroughly and completely.

**Pre-finished Wood:** Clean using commercial floor cleaner to remove any built up waxes and residue. Sand with maroon non-woven pad. Always test for adhesion and performance in a small, hidden area.

**Other Substrates:** Not recommended

**Sanding Between Coats:** If recoating within 24 hours, sanding is not required unless a smoother surface is desired. When needed, use fine (240) sandpaper or maroon non-woven pad.

**System Recommendations:** 3-4 total coats of finish are recommended on raw wood.

**Traffic:** Floors may be carefully walked on (socks only) after 6 hours. Furniture can be replaced (with protective pads) after 3 days. Rugs can be replaced and normal use is safe after 10 days.

**Storage & Shelf Life:** Above 50°F and below 80°F, out of direct sunlight, tightly sealed. Finish preservers such as Bloxygen can help prolong storage life. Best if used within one year of date on can. Unopened and properly stored finish can conservatively last up to 5 years.

**Disposal:** Always dispose of any leftover coatings in accordance with local laws. Do not pour down the drain.

The information and recommendations on this sheet are based upon information gathered at the time of publication and do not act as a safety data sheet. For complete safety and product data, consult the product labels and visit [www.generalfinishes.com](http://www.generalfinishes.com) for complete SDS sheets.

Published March 2020 by General Finishes Corp. East Troy, Wi.

<b>Product Type:</b>	Water-based acrylic/urethane blend
<b>Sheens Available:</b>	Satin (30), Semi-Gloss (55)
<b>Tintable?:</b>	No
<b>Volume Solids:</b>	29%
<b>Weight Solids:</b>	32%
<b>Rec. Film Thickness:</b>	Wet: 3-5 mils Total Dry (multiple coats): 2.5-5 mils
<b>Coverage:</b>	450 sq. ft. per gallon
<b>Viscosity:</b>	Thin (150-300 cPs)
<b>Application:</b>	Recommended using T-bar applicator
<b>Brush:</b>	Pad applicator can be used
<b>Roll:</b>	Microfiber
<b>HVLP:</b>	Not recommended
<b>Air-Assist Airless:</b>	Not recommended
<b>Airless:</b>	Not recommended
<b>Dry Time (touch):</b>	45 minutes
<b>Dry Time (recoat):</b>	2-4 hours
<b>Cure Time:</b>	10 days @ 70°F, 50% humidity
<b>Thin With:</b>	GF Extender
<b>Clean Hands w/:</b>	Soap & Water
<b>Clean Equipment w/:</b>	GF Brush & Gun Cleaner
<b>Sizes Available:</b>	Gallons
<b>VOC:</b>	Under 224 g/L